

### Guardian-Vitro-Cardinal ++ dual

Make-up Name	Glass 1 & Coating	Glass 2 & Coating	Gap 1	Visible Light			Solar Energy						Thermal Properties			Light to Solar Gain (LSG)
				Transmittance	Reflectance		Transmittance	Reflectance		Solar Heat Gain Coefficient (SHGC)	Shading Coefficient (sc)	Relative Heat Gain (RHG)	U-Value		R-Value Winter Night (hr-ft <sup>2</sup> -F/Btu)	
					Visible (τ <sub>v</sub> %)	ρ <sub>v</sub> % out		ρ <sub>v</sub> % in	Solar (τ <sub>e</sub> %)				ρ <sub>e</sub> % out	ρ <sub>e</sub> % in		
Cardinal 180	Guardian Clear Glass (North America)	LoE-180 (IGDB) on Cardinal Clear (IGDB)	10% Air, 90% Argon	79	15	16	60	22	21	0.69	0.79	162	0.260	0.239	3.85	1.14
Climaguard 80/71	Guardian Clear Glass (North America)	ClimaGuard® 80/71 (North America) on Guardian Clear Glass (North America)	10% Air, 90% Argon	80	14	14	62	21	20	0.71	0.81	166	0.265	0.246	3.78	1.13
Vitro Sungate 400	Vitro Clear glass USA (IGDB)	Vitro Sungate® 400 (IGDB) on Vitro Clear glass USA (IGDB)	10% Air, 90% Argon	78	14	14	57	19	18	0.68	0.78	159	0.277	0.264	3.61	1.15

Calculation Standard: NFRC 2010

**Cardinal 180:**

GLASS: Guardian Clear Glass (North America) Glass, 1/8" (3mm) GAP: 10% Air, 90% Argon 1/2" (12.7mm) GLASS: Cardinal Clear (IGDB) Glass, 1/8" (3mm) (3-LoE-180 (IGDB))

**Climaguard 80/71:**

GLASS: Guardian Clear Glass (North America) Glass, 1/8" (3mm) GAP: 10% Air, 90% Argon 1/2" (12.7mm) GLASS: Guardian Clear Glass (North America) Glass, 1/8" (3mm) (3-ClimaGuard® 80/71 (North America))

**Vitro Sungate 400:**

GLASS: Vitro Clear glass USA (IGDB) Glass, 1/8" (3mm) GAP: 10% Air, 90% Argon 1/2" (12.7mm) GLASS: Vitro Clear glass USA (IGDB) Glass, 1/8" (3mm) (3-Vitro Sungate® 400 (IGDB))

Cardinal 180

		Solar Absorp % ( $\alpha_e$ )	Winter Night Temps	Summer Day Temps	R Value (hr-ft <sup>2</sup> -F/Btu)
<b>Outdoors</b>					
GLASS 1	Guardian Clear Glass (North America) #1 -----	-----	Air -0.4	Air 89.6	wint. night Air 0.189 hr-ft <sup>2</sup> -F/Btu
	Thickness = 1/8" (3mm) #2 -----	7.38	3.0	94.6	0.017
GAP 1	10% Air, 90% Argon, 1/2" (12.7mm)	-----	3.4	94.7	2.827
GLASS 2	Cardinal Clear (IGDB) #3 LoE-180 (IGDB)	5.52	54.9	94.5	0.017
	Thickness = 1/8" (3mm) #4 -----	5.02	55.2	94.2	
Total Unit (Nominal) = 3/4 in		Slope = 90°		Window Height =	Air 0.803
				1 meter	3.853
Estimated Nominal Glazing Weight: 3.04 lb/ft <sup>2</sup>					R total
<b>Indoors</b>					

Climaguard 80/71

		Solar Absorp % ( $\alpha_e$ )	Winter Night Temps	Summer Day Temps	R Value (hr-ft <sup>2</sup> -F/Btu)
<b>Outdoors</b>					
GLASS 1	Guardian Clear Glass (North America) #1 -----	-----	Air -0.4	Air 89.6	wint. night Air 0.189 hr-ft <sup>2</sup> -F/Btu
	Thickness = 1/8" (3mm) #2 -----	7.21	3.1	94.4	0.017
GAP 1	10% Air, 90% Argon, 1/2" (12.7mm)	-----	3.4	94.6	2.751
GLASS 2	Guardian Clear Glass (North America) #3 ClimaGuard® 80/71 (North America)	6.04	54.6	93.8	0.017
	Thickness = 1/8" (3mm)	3.99	54.9	93.5	
Total Unit (Nominal) = 3/4 in		Slope = 90°		Window Height =	Air 0.802
				1 meter	3.776
Estimated Nominal Glazing Weight: 3.04 lb/ft <sup>2</sup>					R total
<b>Indoors</b>					

Vitro Sungate 400

				Solar Absorp % ( $\alpha_e$ )	Winter Night Temps	Summer Day Temps	R Value (hr-ft <sup>2</sup> -F/Btu)
Outdoors					Air -0.4	Air 89.6	wint. night Air 0.189 hr-ft <sup>2</sup> -F/Btu
GLASS 1	Vitro Clear glass USA (IGDB)		#1 -----	-----	3.3	97.3	0.019
	Thickness = 1/8" (3mm)		#2 -----	11.41	3.7	97.5	
GAP 1	10% Air, 90% Argon, 1/2" (12.7mm)						2.584
GLASS 2	Vitro Clear glass USA (IGDB)		#3 Vitro Sungate® 400 (IGDB)	6.28	53.9	97.1	0.018
	Thickness = 1/8" (3mm)		#4 -----	5.77	54.2	96.7	
Total Unit (Nominal) = 3/4 in		Slope = 90°	Window Height = 1 meter	57.17 Trans	Air 69.8 (°F)	Air 75.2 (°F)	Air 0.800
Estimated Nominal Glazing Weight: 3.04 lb/ft <sup>2</sup>							3.611 R total
Indoors							

**Important Notes**

Calculations and terms in this report are based on NFRC 2010. The performance values shown above represent nominal values for the center of glass with no spacer system or framing.

Embodied CO<sub>2</sub> [eq. kg/m<sup>2</sup>] A1-A3 is estimated based on material Embodied Carbon Factor (ECF), derived from Guardian Glass Regional third-party independently verified and published / current Environmental Product Declarations (EPDs) which are produced to EN 15804 and are compliant with the requirements of ISO 14044, the International Life Cycle Assessment (LCA) standard, and ISO 14025 and ISO 21930, the international standards covering EPD for construction products. The A1-A3 ECF is an estimate of the embodied carbon due to production of that material. The resulting material value should then be multiplied by the square area of glazing to provide an estimate of embodied carbon of the material at the project scale. Embodied CO<sub>2</sub> estimates provided by Guardian represent only values associated with the glass components manufactured by Guardian. The estimated values do not represent in any way a plant-specific and/or product specific guarantee.

**Laminated products:**

The Performance Calculator allows the user to model a wide variety of laminated glass makeups using different float glass substrates, coatings and interlayer material, including those makeups where the coating faces the interlayer. It is the user's responsibility to assess whether the laminated glass makeup meets relevant regional standards and complies with applicable laminated glass safety regulations.

In addition, when the laminated glass makeup includes a coating facing the interlayer material, there may be a loss of thermal insulation performance and a color change compared to non-embedded coated class.

**Non-specular products (translucent or diffuse):**

The performance measurement for non-specular (translucent or diffuse) materials such as translucent interlayers or acid etched glass surface, or surface with ceramic frit is limited by the current experimental technologies. Since measurements capture physically only a part of the resulting radiation, calculated performance results provided herein and based on such measurements are not compliant with any standard (including EN 410) and may only be used as a general reference. Actual values may vary significantly based upon exact fabrication process, as well as type, thickness and color of used non-specular material.

Please note that the Thermal Stress Guideline is only a general guide to the thermal safety of a glazing, and it is not a replacement for detailed thermal stress analysis.

**Explanation of Terms**

**Visible Light Transmittance (Tv, %)** is the percentage of incident light in the wavelength range of 380 nm to 780 nm that is transmitted by the glass.

**Ultraviolet (UV) Transmittance ( $T_{uv}$ , %)** is the percentage of the incident solar radiation transmitted by the glazing in the 300 nm to 380 nm range.

**Solar Energy Direct Transmittance ( $T_e$ , %)** is the percentage of incident solar energy in the wavelength range of 300 nm to 2500 nm that is directly transmitted by the glass.

**Visible Light Reflectance Outdoors/Indoor ( $R_v$  out/in, %)** is the percentage of incident visible light directly reflected by the glass.

**Solar Direct Reflectance Outdoors/Indoors ( $R_e$  out/in, %)** is the percentage of incident solar energy directly reflected by the glass.

**Solar Energy Absorptance ( $A_e$ , %)** is the percentage of the sun's energy that is absorbed by glass.

**U-Value** is the glazing parameter that characterizes the heat transfer through the central part of the glazing, i.e. without edge effects, and expresses the steady-state density of heat transfer rate per temperature difference between the environmental temperatures on each side. US Standard units are Btu/hr·ft<sup>2</sup>·F and SI / Metric units are W/m<sup>2</sup> K.

**Relative Heat Gain (RHG)** is the total net heat gain to the indoors due to both the air-to-air thermal conductance and the solar heat gain. US Standard units are Btu/hr.ft<sup>2</sup> and SI / Metric units are W/m<sup>2</sup>.

**Shading Coefficient (sc)** is Solar Factor divided by 0.87. It is a measure of the solar heat gain referenced to 3 mm clear glass which has the designated value of 1.00.

**Solar Heat Gain Coefficient (SHGC)** is the sum of the solar direct transmittance and the secondary heat transfer factor of the glazing towards the inside, the latter resulting from heat transfer by convection and longwave IR-radiation of that part of the incident solar radiation which has been absorbed by the glazing.

**Light-to-Solar Gain (LSG)** is the ratio of visible light gain to solar gain.  $LSG = (\text{Visible Transmittance}) / (\text{SHGC})$

**Color Rendering Index in transmission, D65 ( $R_a$ )** is the change in color of an object as a result of the light being transmitted by the glass.

**Weighted Sound Reduction Index ( $R_w$ )** is a single-number quantity which characterizes the airborne sound insulation of a material or building element over a range of frequencies.

**Sound Transmission Class (STC)** is a single-number quantity which characterizes the airborne sound insulation of a material or building element over a range of frequencies.

#### Disclaimer

This performance analysis is provided for the limited purpose of assisting the user in evaluating the performance of the glass products identified on this report.

Spectral data for products manufactured by Guardian reflect nominal values derived from typical production samples or CE Initial Type Testing and subject to variations due to manufacturing and calculation tolerances. Spectral data for products not manufactured by Guardian were derived from the LBNL International Glazing Database and have not been independently verified by Guardian. Guardian recommends a full-size mock-up be approved.

The values provided herein are generated according to established engineering practices and applicable calculation standards. Many factors may affect glazing characteristics, including glass size, building orientation, shading, wind speed, type of installation, production process and others. The applicability and results of the analysis are directly related to user inputs and any changes in actual conditions can have a significant effect on the results. It is the responsibility of the users of the analysis to ensure that the intended application is appropriate and complies with all relevant laws, regulations, standards, codes of practices, processing guidelines and other requirements. Guardian makes no guarantee that any glazing modeled herein is available from Guardian or any other manufacturer. The user has the responsibility to check with the manufacturer regarding availability of any glass type or make-up.

While Guardian has made a good faith effort to verify the reliability of the tools used for this analysis, they may contain unknown programming errors that could result in inaccurate results. The user assumes all risk relating to the results provided and is solely responsible for selection of appropriate products for user's application. Guardian makes no express or implied warranty of any kind with respect to the tools used by Guardian and this analysis. There are no warranties of merchantability, non-infringement or fitness for a particular purpose with respect to the tools used by Guardian and this analysis and no warranty shall be implied by operation of law or otherwise. The only warranties applicable to Guardian products are those separately provided in writing for each product. In no event shall Guardian be liable for direct, indirect, special, consequential

or incidental damages of any kind relating to or resulting from use of Guardian tools and analyses.

Trademarks owned by Guardian Industries, LLC and/or its affiliates may be registered in the United States and other jurisdictions. All other trademarks are property of their respective owners.

User hereby represents and warrants that it is the rightful owner of all intellectual property rights (the "IP Rights") in and to any logos, images, or trademarks user uploads for application in the Guardian Performance Calculator output report. User agrees to indemnify, defend and hold harmless Guardian Industries, LLC and its affiliates, directors, officers, employees, and agents from and against any and all losses, damages, liabilities, claims, demands, suits, judgments, settlements, costs and expenses (including reasonable attorneys' fees and costs) arising out of or in connection with any third-party claim or action that the use of such logos, images or trademarks infringe or misappropriate any other third-party IP Rights. By using a logo, image or trademark, user acknowledges and accepts the terms of this disclaimer and agrees to comply with all applicable laws and regulations governing the use of the logo, image, or trademark.

By accessing this calculator, you agree not to alter or modify the generated report data and information, by any means. Any manual alteration will be your own responsibility and will annul all the content of the report.

Program Version: 4.1.0.9850  
Database Version: 20240229